

**TEST REPORT**

**Client:** Supacolor  
12705 Daphne Ave.  
Hawthorne, CA 90250  
**Attention:** Star Diaz  
**E-Mail:** star@supacolor.com

**Sample Description as Declared :**

Sample Description: Wearable transfer  
Color: Black  
Style # : Not Provided  
Fabric/Garment Weight: Not Provided  
Fiber Content: 100% Cotton  
No. of Samples: 2  
End Use: Not Provided  
Care Instructions: Per Label: Machine Wash Cold with like colors. Only non-chlorine bleach when needed. Tumble dry Low. Warm iron if necessary.  
Sample Received Date: January 24, 2024  
Final Confirmation Date: January 30, 2024  
Test Period: January 30, 2024, February 16, 2024

**OVERALL CONCLUSION:**

Standard  
AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering

Result  
See Results



**For and on behalf of Intertek:**

*Edwin Serrano*

**Intertek**

545 E Algonquin Road, Suite H  
Arlington Heights, Illinois 60005, USA  
Telephone: 847-871-1020 Fax: 847-439-6156



**Test Performed As Requested by Client:**

**TEST RESULTS:**

**1. AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer  
**After 10 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

Multifiber Used: No. 10

<b>Color Staining:</b> (Requirement: 4.0)	<b>Grade:</b>
Acetate Staining	4.5
Cotton Staining	4.5
Nylon Staining	4.5
Polyester/Silk Staining	4.5
Acrylic/Viscose Rayon Staining	4.5
Wool Staining	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 20 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 30 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 40 Washes**

**Select Washing Type**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 50 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory

**Additional Comments:** Slight Print Puckering Observed.



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 60 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory



**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 70 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5 (Slight wash off of Pink print)
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory

**Additional Comments:** Slight Puckering of print observed





**AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

**Sample Description:** Black Wearable Transfer

**After 80 Washes**

**Washing Conditions:** Machine Wash (AATCC) Cold at 80°F, Normal Cycle, Tumble Dry Low, AATCC W/Brightener, 4.0 lbs wash Load, AATCC Type 3 Ballast (50% Cotton/50% Polyester).

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Fabric (Requirement: 3.5)	-
Color Change – Print (if applicable) (Requirement: 3.5)	4.5 (Slight wash off of pink observed)
Color Change – Appliqués/Trims/Linings (if applicable) (Requirement: 3.5)	-
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Visual Evaluation:</b>	<b>Grade:</b>
Hand Feel	Negligible
Abrasion Marks	Negligible

<b>Other Visual Evaluation:</b>	
Delamination/Peeling	Satisfactory
Embellishment Cracking	Satisfactory
Embellishment Puckering	Satisfactory

**Additional Comments:** Slight puckering of print observed



57217 AFTER 10HL	57217 AFTER 20HL	57217 AFTER 30HL
		
57217 AFTER 40HL	57217 AFTER 50HL	57217 AFTER 50HL
		

**Intertek**

545 E Algonquin Road, Suite H  
Arlington Heights, Illinois 60005, USA  
Telephone: 847-871-1020 Fax: 847-439-6156



<p>57217 AFTER 60HL</p> 	<p>57217 AFTER 60HL</p> 	
<p>57217 AFTER 70HL</p> 	<p>57217 AFTER 70HL</p> 	<p>57217 AFTER 70HL</p> 

**Intertek**

545 E Algonquin Road, Suite H  
Arlington Heights, Illinois 60005, USA  
Telephone: 847-871-1020 Fax: 847-439-6156





*The test results stated in this report relate only to the item(s) tested. This test report may not be reproduced except in full, without written approval of Intertek.*



*If you need assistance in interpreting these results or if you have any questions,  
please feel free to call Customer Service Department*

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

**Intertek**

545 E Algonquin Road, Suite H  
Arlington Heights, Illinois 60005, USA  
Telephone: 847-871-1020 Fax: 847-439-6156

